

## ST195

### MATERIAL SAFETY DATA SHEET HOT MELT ADHESIVES

Prepared Date: January 1, 2010

---

#### SECTION I

MANUFACTURED BY: Western American, Inc  
1518 Taney Street  
North Kansas City, MO 64116

TELEPHONE: 816-421-3000  
CONTACT: Rick Hennig

PRODUCT CLASS: Hot Melt Adhesive  
MANUFACTURER'S CODES: **ST195**

---

#### SECTION II - HAZARDOUS INGREDIENTS

Paraffin Wax Fume CAS# 8002-74-2 NIOSH REL: TWA 2mg/m<sup>3</sup>  
ACGIH TLV: 2mg/m<sup>3</sup> (TWA)

---

#### SECTION III - PHYSICAL DATA

BOILING POINT - N/A SPECIFIC GRAVITY - 0.92  
VAPOR PRESSURE - N/A MELTING POINT - 160 - 230  
VAPOR DENSITY - N/A EVAPORATION RATE - N/A  
SOLUBILITY IN WATER - INSOLUBLE  
APPEARANCE AND ODOR - AMBER STICKS

---

#### SECTION IV - FIRE AND EXPLOSION HAZARD DATA

DOT CATEGORY - NON FLAMMABLE FLASH POINT - 450F  
EXTINGUISHING MEDIA - CO<sub>2</sub>

SPECIAL FIRE FIGHTING PROCEDURES - NONE  
UNUSUAL FIRE AND EXPLOSION HAZARDS - NONE

---

#### SECTION V - HEALTH HAZARD DATA

MAIN ROUTE OF ENTRY - INHALATION, PROVIDE ADEQUATE VENTILATION  
TARGET ORGANS - NONE  
HEALTH HAZARDS (ACUTE AND CHRONIC) - NONE  
CONTACT WITH MOLTEN MATERIAL WILL CAUSE THERMAL BURNS TO SKIN AND EYES

#### FIRST AID:

**COOL AFFECTED AREA IMMEDIATELY, OBTAIN MEDICAL ASSISTANCE, DO NOT ATTEMPT TO REMOVE COOLED ADHESIVE FROM SKIN, AS IT WILL SEVERELY DAMAGE SKIN**

## ST195

---

### SECTION VI - REACTIVITY DATA

---

STABILITY - STABLE

HAZARDOUS DECOMPOSITION OR BY-PRODUCTS - CARBON MONOXIDE

CONDITIONS TO AVOID - TEMPERATURES OVER 400F MAY CAUSE RESIN  
DEGRADATION

HAZARDOUS POLYMERIZATION - CANNOT OCCUR

---

### SECTION VII - SPILL OR LEAK PROCEDURES

---

SPILL - SWEEP UP MATERIAL TO PREVENT SLIPPING, ALLOW MOLTEN SPILLS TO COOL  
BEFORE SCRAPING UP AND DISPOSING.

WASTE DISPOSAL METHOD - IN ACCORDANCE WITH LOCAL  
REGULATIONS

---

### SECTION VIII - PROTECTIVE EQUIPMENT TO BE USED

---

VENTILATION - YES, PROVIDE ADEQUATE VENTILATION, DO NOT USE IN CONFINED  
SPACES

PROTECTIVE GLOVES - YES

EYE PROTECTION - YES

---

### SECTION IX - PRECAUTIONS OR OTHER COMMENTS

---

STORAGE AND HANDLING - STORE IN COOL DRY PLACE, OPTIMUM  
TEMPERATURE 70 F.

PICK UP MATERIAL IMMEDIATELY TO ELIMINATE SLIPPING HAZARDS.